



PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with A1 5360 MIM000600 specification requirements.

TGC Part Number	4605-374
Weight, psf (kg/m ²)	0.605 (2.95)
Warpage, in/ft (mm/m)	0 (0)
Long Beam Bending, lb (N)	350 (1,556)
Deflection @ 100 lbs, inch (@445N, mm)	0.370 (9.42)
Drum Peel, in-lb/3" width (N/76mm width)	78 (347)
Flammability	Meet requirements of FAR 25.853 Appendix F Part I (a)(1)(i) & (a)(2)(ii)

Figures shown reflect typical values and should not be used as design specifications.

updated

All recommendations, statements, values and technical data herein are based on tests The Gill Corporation believes to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. Users shall rely on their own information and tests to determine suitability of the product for the intended use and assume all risks and liability resulting from their use of the product. The Gill Corporation's sole responsibility shall be to replace that portion of the product that proves to be defective. The Gill Corporation will not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations or statements not contained in a written agreement signed by an officer of The Gill Corporation shall not be binding upon The Gill Corporation. Gillfab® and Gillcore® are registered trademarks of The Gill Corporation.