


Gillfab® 5142



PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with MIL STD 401B and ASTM standard method.

TGC Part Number	5142
Panel Weight, psf (kg/m ²)	0.63 (3.08)
Panel Thickness, inch (mm)	0.390 (10.2)
Skin Thickness, face/back, inch (mm)	0.016/0.010 (0.406/0.279)
Climbing Drum Peel, in-lbs/3" width (N-m/76mm width)	49 (5.54)
Climbing Drum Peel after humidity conditioned, in-lbs/3" width (N-m/76mm width)	49 (5.54)