

Sandwich Panels Composed of Fiberglass Reinforced Epoxy Facing Bonded to a Nomex[®] Aramid Honeycomb Core

Ùæ~^c^ÁÖæcæÁÙ@^^Á

æ&&[!âi)*k[ÁØ^á^æ|ÁÜ^*i*c^!ÁDÁX[!ÉÁ T T ÉÁ P [ÉÁ í !ÁDÁ T [)áæ~ÉÁ T æ!&@!G T ÉÁ G e F G ÁDÁ Ü * |Á•Áæ) á!Ü^*~|æc[]•

SECTION 3: Composition/information on ingredients

Òç][[•â[]Á@æ:æ!âÁ

KÁ Ôæ}Áâ^&[{] [•^Áâ}Áæâ-â!^Á^ { äccä } *Ác [çä&Á- { ^•Áæ } äÁ *æ•^Á [-Á&æ!à [] Áâ [çä^É&æ!à [] Á { [] [çä^ÉÁ @^á! [*^) Á&^æ } äâ^É&æ } çä { [] ^Á [çä^Á•ÉÁ@^á! [*^) Áâ! [{ äâ^ÉÁ [çä^Á•Á [-Á] äc! [*^) Á [ç@^!Ác [çä&Áæ } äÁ ä! : äccä } *Á *æ•^Á•Á&æ } Áâ^Á! : [ä~&^Á!Á^) ä! } *Á [] Á& [] äccä [] Á [-Á& [{ ä~•cä [] ÉÁ

Ü^æ&cäçäc^Á

KÁ Þ [ç!^æ&cäç^Á~ } ä^!Á] [: { æ!Á~•^Áæ } äÁ& [] äccä [] •ÉÁ

5.3. Advice for firefighters

Øä!^-ä*çä } *Áâ } •c!~&cä [] •Á

KÁ Ôçæ&~æc^Áæ!^æÉÁ

Ú! [ç^&cä [] Áâ~!ä } *Á-ä!^-ä*çä } *Á

KÁ Ö [Á] [ç!Á) ç^!Á-ä!^Áæ!^æÁ , äc@ [~ ç!] [] ^!Á] : [ç^&cäç^Á^~ä] { ^) çÉ!ä } &!~ ä! } *Á!^•] ä!æc [!^Á] : [ç^&cä [] ÉÁ Øä!^-ä*çä!^•Á•@ [~!ä , ^æ!Áæ!ÞQUÚP!æ] : [ç^á!~||É-æ&^Á] ä^&^Á•^!-É& [] çæä } ^á!à!^æc@ä } *Áæ] æ!æc~•Á ÇÚÓÓÇÉDÁ [] ^!æc^!ä!ä } Á] [•äcäç^Á] : ^•~!^Á { [ä^Áæ } äÁ-~||Ác~!] [~ ç! [!ä~ } \^!Á^•^æ!ÉÁ

Uç@^!Áâ } - [: { æcä [] } Á

KÁ Q-Áææ } \É! : æ!Á&æ!Á [!Áçæ } \Ác!~&\Áâ•Áâ } ç [[ç^á!ä } Áæ!-ä!^ÉÁQUŠÇEVÖÁ- [!Á] ∈ÉÁ { ^c^!•ÁçFBGÁ { ä!^D!ä } Áæ||Á

Fiberglass (6597-17-3)

CEÔÓ:ΠΑ

P [cÁæ]] |ã&æà|^Á

UÙPCEÁ

UÙPCEÁÚÓŠÁÇVY CEDÁÇ { *D { DÁ

SECTION 9: Physical and chemical properties

9.1. Information on basic physical and chemical properties

Ú@^•î&æ Á•cæc^Á	KÁ Ù [jàÁ
Œ]]^æ!æ}&^Á	KÁ Ùæ}á , î&@Á]æ }^ÉÁ
Ô[[[iÁ	KÁ Ši* @cÁ *!æ^Á
Uâ[iÁ	KÁ Ù j* @cÁ
Uâ[iÁc@i^• @ [jàÁ	KÁ Þ [ÁâæcæÁæçæj æà ^Á
]PÁ	KÁ Þ [ÁâæcæÁæçæj æà ^Á
Ü^ æcç^Á^çæ [iæcâ [}Á iæc^Áçâ ~ c^ Áæ&^cæc^MFDA	KÁ Þ [ÁâæcæÁæçæj æà ^Á
T^ cá} *Á] [â}cÁ	KÁ Þ [ÁâæcæÁæçæj æà ^Á
Ø!^^:â} *Á] [â}cÁ	KÁ Þ [ÁâæcæÁæçæj æà ^Á

